



MANUFACTURING A SOFT SOCKET

COPSIL SOCKET

RTV-2 SILICONE RESIN FOR SOFT SOCKETS

- ✓ Skin contact (ISO 10993-5 standard)
- ✓ Comfort, elasticity dynamism
- ✓ Same injection system as for rigid socket
- ✓ Viscosity adapted to stratification
- ✓ Safe use in the workshop
- ✓ Optimal working time

Product Information



 230b Route des Bouveries 26190 Saint-Nazaire-en-Royans France

 www.cop-chimie.com

 contact@cop-chimie.com

 + 33 (0) 475 487 720

*This flyer was designed using the resources of Flaticon.com and printed by Activ' Graphic.
Do not litter*

CHARACTERISTICS OF THE LIQUID PRODUCT

Aspect	Liquid product, lightly translucent
Viscosity at 20 °C	Mixing: 4,000 mPa.s approx.
Mixing ratio in weight	1 : 1
Working time at 20 °C	approx. 30 min
Demolding time at 20 °C	1 h

CHARACTERISTICS OF THE POLYMERIZED PRODUCT

Final Hardness	38 Sh A
----------------	---------

PACKAGING

1 kg kit	500 g + 500 g
10 kg kit	5 kg + 5 kg
50 kg kit	25 kg + 25 kg
Cartridges	200 ml + 200 ml



User guide available upon request
from your sales contact

 230b Route des Bouveries 26190 Saint-Nazaire-en-Royans France

 www.cop-chimie.com

 contact@cop-chimie.com

 + 33 (0) 475 487 720

*This flyer was designed using the resources of Flaticon.com and printed by Activ' Graphic.
Do not litter*