



MANUFACTURING OF A SOFT SILICONE SOCKET

COPSIL SOCKET

RTV-2 SILICONE RESIN FOR SOFT SOCKETS

- ✓ Skin contact (ISO 10993-5 standard)
- ✓ Comfort, elasticity dynamism
- ✓ Same injection system as for rigid socket
- ✓ Viscosity adapted to stratification
- ✓ Safe use in the workshop
- ✓ Optimal working time

Product Information



📍 230b Route des Bouveries 26190 Saint-Nazaire-en-Royans France

🌐 www.cop-chimie.com

✉ contact@cop-chimie.com

☎ +33 (0) 475 487 720

This flyer was designed using the resources of Flaticon.com and printed by Activ' Graphic.

Do not litter

CHARACTERISTICS OF THE LIQUID PRODUCT

Aspect	Liquid product, lightly translucent
Viscosity at 20 °C	Mixing: 3,250 mPa.s
Mixing ratio in weight	1 : 1
Working time at 20 °C	30 min
Demolding time at 20 °C	1 h

CHARACTERISTICS OF THE POLYMERIZED PRODUCT

Final Hardness	40 Shore A
----------------	------------

PACKAGING

Products	Packaging	References
COPSIL SOCKET	KIT 1 KG (500 g + 500 g)	CSS 01
COPSIL SOCKET	KIT 10 KG (5 KG + 5 KG)	CSS 10
COPSIL SOCKET	KIT 50 KG (25 kg + 25 kg)	CSS 50
COPSIL SOCKET	CARTRIDGE 2 X 200 ML	CSS C400

