

ERGOPEAU

ERGOPEAU is a polyurethane paint that allows the realization of a resistant, elastic and waterproof (but not airtight) skin, with a smooth and satin finish. You can change its finish according to how it is sprayed. ERGOPEAU is aimed to protect, finish or decorate soft or rigid materials.

ERGOPEAU is a white opaque liquid, very fluid and ready-to-use. It can be colored in various shades by adding in the resin our coloring agents in paste (white, black, green, blue, yellow, orange, red, dark or light flesh). It is usually sprayed but can also be applied with a brush in thin layers to remove the sticky effect of certain polyurethane gels.

This paint has a very good grip on the soft polyurethane foams. It can be used without a primary grip coating. Its final drying time is 24 hours.

For substrates other than PU, please use beforehand our sprayable primary ERGOPEAU PRIMAIRE.

Here are the advantages ERGOPEAU provides:

- Limited odor
- Control of toxicity (ERGOFLEX is not labelled Carcinogenic, Mutagenic, Reprotoxic)
- Good mechanical properties (high elasticity, tear resistance)
- Waterproof
- No shrinkage

ERGOPEAU is designed to make protection, finishing, decoration and sealing of foams and rigid or flexible PU elastomers.



Technical characteristics

Density g/L: 840

Dry extract %: 14 to 18

Viscosity mPa.s: 170

Basic smell: acetone

Basic color: white opaque

Basic principle concerning the use of ERGOPEAU paint

1 - Weigh the quantity of coloring agent to put in the paint. Do not exceed 2% in weight (e.g. 10 g of coloring agent for 500 g of paint). Indeed, a dye is a pigment (mineral or organic) impasted with a resin that should not generate a parasitic reaction during the crosslinking of the film. Well mixed, the product is ready for use. This mixture can be stored for several days if stored in bulk, well-closed and protected from moisture.

2 - The purpose of the first veil is to impregnate the foam or the fabric to create a mechanical bonding between the paint and the material. For this, place the gun at 10 cm from the surface to be covered with a pressure of 5 to 6 bar, so that the paint is still "wet" on the support.

3 - The aim of the second layer is to create an elastic and resilient skin thanks to a tangle of yarns like a spider's web, in order to close the cells of the foam. For this, place the gun at 25/30 cm from the support and adjust the opening of the gun to obtain a jet of about 10 cm. The painting must arrive dry on the support. Apply between 4 and 6 cross-passages.

4 - The aim of the third layer is to increase the thickness of the skin. For this, place yourself at 25/30 cm from the surface and increase the material flow to be slightly wet on the support. The thickness of the paint layer is not a problem. If you want to put a thick layer in some places (for various reasons, solidity for example) or to smooth a surface roughness it is better to do it in a single pass crossing the projections of 45°.

The thicker the paint layer, the stronger the resulting film will be but it will lose in elasticity.

The drying time of ERGOPEAU is about 24 hours to obtain a film with optimal mechanical properties.

Handling and safety

ERGOPEAU paint contains active polymers that are carried by solvents that evaporate very quickly. Solvents' vapors present a double risk: they are highly flammable and more or less harmful to inhale. Use the product away from any flame or source of ignition (especially do not use hot air guns to accelerate the evaporation of the solvent).

Work in well ventilated rooms, in order not to breathe vapors that appear at room temperature and use extraction systems suitable for flammable products next to the spray stations. In addition, use protective gloves, safety glasses and appropriate masks.

Finally, please read the safety information on the cans and the safety data sheets.

Storage and packaging

The ERGOPEAU paint is guaranteed for 18 months if stored between 18°C and 25°C in hermetic container, away from moisture and light. The ERGOPEAU is available in various packaging. Taps are available for purchase for larger packaging.

	REFERENCE	PACKAGING
ERGOPEAU COATING	EGE3 R01	1 L
	EGE3 R05	5 L
	EGE3 R25	25 L
	EGE3 R57	57 L
TAP FOR 30 L CAN	ROB 004	Per unit
	ROB 014	Pack of 10
TAP FOR 60 L AND 200 L DRUMS	ROB 001	Per unit

Custom's code

ERGOPEAU RESIN

35069100